

Table 1-a – STRUCTURAL LIGHT FRAMING, STRUCTURAL JOISTS AND PLANKS, AND STUDS - 2" TO 4" THICK (Each width has a separate set of design values)

GRADE	Extreme Fiber in Bending "F_b"	Tension Parallel to Grain "F_t"	Horizontal Shear "F_v"	Compression Perpendicular to Grain "F_{c⊥}"	Compression Parallel to Grain "F_c"	Modulus of Elasticity (million psi) "E"
Kiln Dried or S-Dry, MC 15, MC 19						
APPLIES TO 2" - 4" THICK – 2" - 4" WIDE ONLY						
Dense Select Structural	2700	1900	175	660	2050	1.9
Select Structural	2350	1650	175	565	1900	1.8
Non Dense Select Structural	2050	1450	175	480	1800	1.6
No. 1 Dense	1650	1100	175	660	1750	1.8
No. 1	1500	1000	175	565	1650	1.6
No. 1 Non Dense	1300	875	175	480	1550	1.4
No. 2 Dense	1200	750	175	660	1500	1.6
No. 2	1100	675	175	565	1450	1.4
No. 2 Non Dense	1050	600	175	480	1450	1.3
No. 3 and Stud	650	400	175	565	850	1.3

A5





Table 1-b – STRUCTURAL LIGHT FRAMING, STRUCTURAL JOISTS AND PLANKS, AND STUDS -2” TO 4” THICK (Each width has a separate set of design values)

GRADE	Extreme Fiber in Bending “F_b”	Tension Parallel to Grain “F_t”	Horizontal Shear “F_v”	Compression Perpendicular to Grain “F_{c⊥}”	Compression Parallel to Grain “F_c”	Modulus of Elasticity (million psi) “E”
Kiln Dried or S-Dry, MC 15, MC 19						
APPLIES TO 2” - 4” THICK – 5” - 6” WIDE ONLY						
Dense Select Structural	2400	1650	175	660	1900	1.9
Select Structural	2100	1450	175	565	1800	1.8
Non Dense Select Structural	1850	1300	175	480	1700	1.6
No. 1 Dense	1500	1000	175	660	1650	1.8
No. 1	1350	875	175	565	1550	1.6
No. 1 Non Dense	1200	775	175	480	1450	1.4
No. 2 Dense	1050	650	175	660	1450	1.6
No. 2	1000	600	175	565	1400	1.4
No. 2 Non Dense	950	525	175	480	1350	1.3
No. 3 and Stud	575	350	175	565	800	1.3

Table 1-c – STRUCTURAL LIGHT FRAMING, STRUCTURAL JOISTS AND PLANKS, AND STUDS -2” TO 4”THICK (Each width has a separate set of design values)

GRADE	Extreme Fiber in Bending “F_b”	Tension Parallel to Grain “F_t”	Horizontal Shear “F_v”	Compression Perpendicular to Grain “F_{c⊥}”	Compression Parallel to Grain “F_{c∥}”	Modulus of Elasticity (million psi) “E”
Kiln Dried or S-Dry, MC 15, MC 19						
APPLIES TO 2” - 4” THICK – 8” WIDE ONLY (1)						
Dense Select Structural	2200	1550	175	660	1850	1.9
Select Structural	1950	1350	175	565	1700	1.8
Non Dense Select Structural	1700	1200	175	480	1650	1.6
No. 1 Dense	1350	900	175	660	1600	1.8
No. 1	1250	800	175	565	1500	1.6
No. 1 Non Dense	1100	700	175	480	1400	1.4
No. 2 Dense	975	600	175	660	1400	1.6
No. 2	925	550	175	565	1350	1.4
No. 2 Non Dense	875	500	175	480	1300	1.3
No. 3 and Stud	525	325	175	565	775	1.3

A7





Table 1-d – STRUCTURAL LIGHT FRAMING, STRUCTURAL JOISTS AND PLANKS, AND STUDS -2” TO 4” THICK (Each width has a separate set of design values)

GRADE	Extreme Fiber in Bending “F_b”	Tension Parallel to Grain “F_t”	Horizontal Shear “F_v”	Compression Perpendicular to Grain “F_{c⊥}”	Compression Parallel to Grain “F_c”	Modulus of Elasticity (million psi) “E”
Kiln Dried or S-Dry, MC 15, MC 19						
APPLIES TO 2” - 4” THICK – 10” WIDE ONLY (1)						
Dense Select Structural	1950	1300	175	660	1800	1.9
Select Structural	1700	1150	175	565	1650	1.8
Non Dense Select Structural	1500	1050	175	480	1600	1.6
No. 1 Dense	1200	800	175	660	1550	1.8
No. 1	1050	700	175	565	1450	1.6
No. 1 Non Dense	950	625	175	480	1400	1.4
No. 2 Dense	850	525	175	660	1350	1.6
No. 2	800	475	175	565	1300	1.4
No. 2 Non Dense	750	425	175	480	1250	1.3
No. 3 and Stud	475	275	175	565	750	1.3

A8

Table 1-e – STRUCTURAL LIGHT FRAMING, STRUCTURAL JOISTS AND PLANKS, AND STUDS -2” TO 4” THICK (Each width has a separate set of design values)

GRADE	Extreme Fiber in Bending “F_b”	Tension Parallel to Grain “F_t”	Horizontal Shear “F_v”	Compression Perpendicular to Grain “F_{c⊥}”	Compression Parallel to Grain “F_c”	Modulus of Elasticity (million psi) “E”
Kiln Dried or S-Dry, MC 15, MC 19						
APPLIES TO 2” - 4” THICK – 12” WIDE ONLY (1), (2)						
Dense Select Structural	1800	1250	175	660	1750	1.9
Select Structural	1600	1100	175	565	1650	1.8
Non Dense Select Structural	1400	975	175	480	1550	1.6
No. 1 Dense	1100	750	175	660	1500	1.8
No. 1	1000	650	175	565	1400	1.6
No. 1 Non Dense	900	575	175	480	1350	1.4
No. 2 Dense	800	500	175	660	1300	1.6
No. 2	750	450	175	565	1250	1.4
No. 2 Non Dense	700	400	175	480	1250	1.3
No. 3 and Stud	450	250	175	565	725	1.3

A9





A10

Table 3 – LIGHT FRAMING – 2” TO 4” THICK

GRADE	Extreme Fiber in Bending “F_b”	Tension Parallel to Grain “F_t”	Horizontal Shear “F_v”	Compression Perpendicular to Grain “F_{cL}”	Compression Parallel to Grain “F_{cP}”	Modulus of Elasticity (million psi) “E”
Kiln Dried or S-Dry, MC 15, MC 19						
<i>APPLIES TO 2” - 4” THICK – 2” - 4” WIDE</i>						
Construction	875	500	175	565	1600	1.4
Standard	475	275	175	565	1300	1.2
Utility *	225	125	175	565	850	1.2

*Design values apply to 4” widths only.

Table 4-a – TIMBERS – 5” x 5” AND LARGER

GRADE	Extreme Fiber in Bending “F_b”	Tension Parallel to Grain “F_t”	Horizontal Shear “F_v”	Compression Perpendicular to Grain “F_{c⊥}”	Compression Parallel to Grain “F_{c∥}”	Modulus of Elasticity (million psi) “E”
<i>APPLIES TO 5” x 5” AND LARGER</i>						
Dense Select Structural	1750	1200	165	440	1100	1.6
Select Structural	1500	1000	165	375	950	1.5
No. 1 Dense	1550	1050	165	440	975	1.6
No. 1	1350	900	165	375	825	1.5
No. 2 Dense	975	650	165	440	625	1.3
No. 2	850	550	165	375	525	1.2

A11





Table 5 – DECKING – 2” TO 4” THICK, 2” AND WIDER - (For flatwise use only. See footnote 4.)

GRADE	Extreme Fiber in Bending “F_b”	Compression Perpendicular to Grain “F_{c⊥}”	Modulus of Elasticity (million psi) “E”
Kiln Dried or S-Dry, MC 15, MC 19			
APPLIES TO 2” TO 4” THICK			
Dense Standard Decking	2000	660	1.8
Select Decking	1400	565	1.6
Dense Select Decking	1650	660	1.6
Commercial Decking	1400	565	1.6
Dense Commercial Decking	1650	660	1.6
MC Over 19%			
APPLIES TO 2-1/2” TO 4” THICKNESSES			
Dense Standard Decking	1600	440	1.6
Select Decking	1150	375	1.4
Dense Select Decking	1350	440	1.4
Commercial Decking	1150	375	1.4
Dense Commercial Decking	1350	440	1.4

**Table 6 – MIXED SOUTHERN PINE (Virginia Pine and Pond Pine)
STRUCTURAL LIGHT FRAMING, STRUCTURAL JOISTS AND PLANKS, AND STUDS – 2” TO 4”
THICK (Each width has a separate set of design values)**

GRADE	Extreme Fiber in Bending “F_b”	Tension Parallel to Grain “F_t”	Horizontal Shear “F_v”	Compression Perpendicular to Grain “F_{cL}”	Compression Parallel to Grain “F_c”	Modulus of Elasticity (million psi) “E”
Kiln Dried or S-Dry, MC 15, MC 19						
<i>APPLIES TO 2” TO 4” THICK – 2” – 4” WIDE ONLY</i>						
Select Structural	2050	1200	175	565	1800	1.6
No. 1	1450	875	175	565	1650	1.5
No. 2	1100	675	175	565	1450	1.4
No. 3 and Stud	650	400	175	565	850	1.2
<i>APPLIES TO 2” TO 4” THICK – 5” – 6” WIDE ONLY</i>						
Select Structural	1850	1100	175	565	1700	1.6
No. 1	1300	750	175	565	1550	1.5
No. 2	1000	600	175	565	1350	1.4
No. 3 and Stud	575	350	175	565	775	1.2





Table 6 – MIXED SOUTHERN PINE (Virginia Pine and Pond Pine) -STRUCTURAL LIGHT FRAMING, STRUCTURAL JOISTS AND PLANKS, AND STUDS – 2” TO 4” THICK (Each width has a separate set of design values)

GRADE	Extreme Fiber in Bending “F_b”	Tension Parallel to Grain “F_t”	Horizontal Shear “F_v”	Compression Perpendicular to Grain “F_{c⊥}”	Compression Parallel to Grain “F_c”	Modulus of Elasticity (million psi) “E”
Kiln Dried or S-Dry, MC 15, MC 19						
APPLIES TO 2” TO 4” THICK – 8” WIDE ONLY (1)						
Select Structural	1750	1000	175	565	1600	1.6
No. 1	1200	700	175	565	1450	1.5
No. 2	925	550	175	565	1350	1.4
No. 3 and Stud	525	325	175	565	800	1.2
APPLIES TO 2” TO 4” THICK – 10” WIDE ONLY (1)						
Select Structural	1500	875	175	565	1600	1.6
No. 1	1050	600	175	565	1450	1.5
No. 2	800	475	175	565	1300	1.4
No. 3 and Stud	475	275	175	565	750	1.2
APPLIES TO 2” TO 4” THICK – 12” WIDE ONLY (1),(2)						
Select Structural	1400	825	175	565	1550	1.6
No. 1	975	575	175	565	1400	1.5
No. 2	750	450	175	565	1250	1.4
No. 3 and Stud	450	250	175	565	725	1.2

Table 7 –MIXED SOUTHERN PINE (Virginia Pine and Pond Pine) - LIGHT FRAMING -- 2” TO 4” THICK

GRADE	Extreme Fiber in Bending “F_b”	Tension Parallel to Grain “F_t”	Horizontal Shear “F_v”	Compression Perpendicular to Grain “F_{cL}”	Compression Parallel to Grain “F_{cl}”	Modulus of Elasticity (million psi) “E”
Kiln Dried or S-Dry, MC 15, MC 19						
APPLIES TO 2” - 4” THICK – 2” - 4” WIDE						
Construction	850	500	175	565	1600	1.3
Standard	475	275	175	565	1300	1.2
Utility *	225	125	175	565	850	1.1

* Design values apply to 4” widths only.





Table 8.a – MIXED SOUTHERN PINE (Virginia Pine and Pond Pine) – TIMBERS – 5" x 5" AND LARGER

GRADE	Extreme Fiber in Bending "F_b"	Tension Parallel to Grain "F_t"	Horizontal Shear "F_v"	Compression Perpendicular to Grain "F_{c⊥}"	Compression Parallel to Grain "F_{c∥}"	Modulus of Elasticity (million psi) "E"
<i>APPLIES TO 5" x 5" AND LARGER</i>						
Select Structural	1500	1000	165	375	900	1.3
No. 1	1350	900	165	375	800	1.3
No. 2	850	550	165	375	525	1.0

CONVERSION FACTORS FOR DETERMINING SPRUCE PINE AND SAND PINE DESIGN VALUES

Design Category:	Extreme Fiber in Bending "F _b "	Tension Parallel to Grain "F _t "	Horizontal Shear "F _v "	Compression Perpendicular to Grain "F _{c⊥} "	Compression Parallel to Grain "F _{c//} "	Modulus of Elasticity (million psi) "E"
Spruce Pine Factor	0.78	0.78	0.98	0.73	0.78	0.82
Sand Pine Factor	1.0	1.0	1.0	1.0	1.0	0.84

To obtain a recommended design value for spruce pine or sand pine, multiply the design value for the corresponding grade of Mixed Southern Pine by the appropriate conversion factor. Resulting values may be rounded to the nearest whole number.



**Table 9a – BALDCYPRESS - 2" TO 4" THICK
STRUCTURAL LIGHT FRAMING, STRUCTURAL JOISTS AND PLANKS, AND STUDS**

GRADE	Extreme Fiber in Bending (psi) "F_b"	Tension Parallel to Grain (psi) "F_t"	Horizontal Shear (psi) "F_v"	Compression Perpendicular to Grain (psi) "F_{c⊥}"	Compression Parallel to Grain (psi) "F_{c∥}"	Modulus of Elasticity (million psi) "E"
Kiln Dried or S-Dry, MC 15, MC 19						
Sel Str	1200	650	160	615	1200	1.4
No. 1	1000	550	160	615	1050	1.4
No. 2	825	450	160	615	900	1.3
No. 3	475	250	160	615	525	1.2
Stud	650	350	160	615	575	1.2
Construction	925	500	160	615	1100	1.2
Standard	525	275	160	615	925	1.1
Utility	250	125	160	615	600	1.0

Table 9b – SIZE FACTORS, C_F - MULTIPLY THE TABULATED DESIGN VALUE BY THE FOLLOWING SIZE FACTORS TO OBTAIN VALUES FOR THE INDICATED WIDTH

Grades	Width (depth)	"F _b "		"F _t "	"F _{cl} "
		Thickness (breadth)			
		2" & 3"	4"		
Sel Str, No. 1, No. 2, and No. 3	2", 3" & 4"	1.5	1.5	1.5	1.5
	5"	1.4	1.4	1.4	1.1
	6"	1.3	1.3	1.3	1.1
	8"	1.2	1.3	1.2	1.05
	10"	1.1	1.2	1.1	1.0
	12"	1.0	1.1	1.0	1.0
	14" & wider	0.9	1.0	0.9	0.9
Stud	2", 3" & 4"	1.1	1.1	1.1	1.05
	5" & 6"	1.0	1.0	1.0	1.0
	8" & wider	Use No.3 grade design values and factors			
Construction and Standard	2", 3" & 4"	1.0	1.0	1.0	1.0
Utility	4"	1.0	1.0	1.0	1.0
	2" & 3"	0.4		0.4	0.6





**Table 9c – BALDCYPRESS
TIMBERS – 5" x 5" AND LARGER**

GRADE	Extreme Fiber in Bending (psi) "F_b"	Tension Parallel to Grain (psi) "F_t"	Horizontal Shear (psi) "F_v"	Compression Perpendicular to Grain (psi) "F_{cL}"	Compression Parallel to Grain (psi) "F_{c//}"	Modulus of Elasticity (million psi) "E"
APPLIES TO 5" x 5" AND LARGER						
Sel Str	1150	750	200	615	1050	1.3
No. 1	1000	675	200	615	925	1.3
No. 2	625	425	175	615	600	1.0

A20

Table 10.a – Southern Pine From Misiones Argentina - Free of Heart Center & Medium Grain Density¹

GRADE	Extreme Fiber in Bending (psi) "F_b"	Tension Parallel To Grain (psi) "F_t"	Shear Parallel-to-Grain (psi) "F_v"	Compression Perpendicular to Grain (psi) "F_{c⊥}"	Compression Parallel to Grain (psi) "F_{c∥}"	Modulus of Elasticity "E(10⁶ psi)"
Kiln Dried or S-Dry, MC 15, MC 19						
Select Structural	1700	775	210	710	1250	1.5
No. 1	1150	525	210	710	1150	1.5
No. 2	1000	450	210	710	1100	1.5
No. 3	575	250	210	710	650	1.4
Stud	800	350	210	710	700	1.4
Construction	1150	525	210	710	1350	1.4
Standard	650	300	210	710	1150	1.3
Utility	300	125	210	710	750	1.2

¹ The base design values for the characteristic size of 2"x12"x144", 2"x6"x120" for stud, and 2"x4"x144" for Construction, Standard, and Utility.



Table 10.b – Southern Pine From Misiones Argentina ¹ - Base Design Values

GRADE	Extreme Fiber in Bending (psi) "F_b"	Tension Parallel To Grain (psi) "F_t"	Shear Parallel-to- Grain (psi) "F_v"	Compression Perpendicular to Grain (psi) "F_{cL}"	Compression Parallel to Grain (psi) "F_{cII}"	Modulus of Elasticity "E(10⁶ psi)"
Kiln Dried or S-Dry, MC 15, MC 19						
Select Structural	1100	500	150	440	1150	1.2
No. 1	775	350	150	440	1000	1.1
No. 2	725	325	150	440	950	1.1
No. 3	425	200	150	440	550	0.9
Stud	575	250	150	440	600	0.9
Construction	825	375	150	440	1150	1.0
Standard	475	200	150	440	975	0.9
Utility	225	100	150	440	650	0.8

¹ The base design values for the characteristic size of 2'x12"x144", 2"x6"x120" for stud, and 2"x4"x144" for Construction, Standard, and Utility.

Table 10.c – SIZE FACTORS, C_F - MULTIPLY THE TABULATED DESIGN VALUE BY THE FOLLOWING SIZE FACTORS TO OBTAIN VALUES FOR THE INDICATED WIDTH.

Grades	Width (depth)	"F _b "		"F _t "	"F _{cl} "
		Thickness (breadth)			
		2" & 3"	4"		
Sel Str, No. 1, No. 2, and No. 3	2", 3" & 4"	1.5	1.5	1.5	1.5
	5"	1.4	1.4	1.4	1.1
	6"	1.3	1.3	1.3	1.1
	8"	1.2	1.3	1.2	1.05
	10"	1.1	1.2	1.1	1.0
	12"	1.0	1.1	1.0	1.0
	14" & wider	0.9	1.0	0.9	0.9
Stud	2", 3" & 4"	1.1	1.1	1.1	1.05
	5" & 6"	1.0	1.0	1.0	1.0
	8" & wider	Use No.3 grade design values and factors			
Construction and Standard	2", 3" & 4"	1.0	1.0	1.0	1.0
Utility	4"	1.0	1.0	1.0	1.0
	2" & 3"	0.4		0.4	0.6

DESIGN VALUES FOOTNOTES (1-12)

- (1) For 4" thick material that is 8" or greater in width, the F_b value may be multiplied by 1.1.
- (2) For sizes wider than 12", use 90% of the F_b , F_t , and $F_{C//}$ specified for the 12" width. Use 100% of the F_v , $F_{C\perp}$ (perpendicular-to-grain), and MOE specified for the 12" width.
- (3) In construction where three or more load-carrying members such as joists, rafters, studs or decking are contiguous or are spaced not more than 24 inches in frame construction and are joined by transverse floor, roof or other load distributing elements, an increase in bending stress of 15 percent for members used in such systems is allowed as a design consideration, as provided in ASTM D1990.
- (4) For flatwise use, the following adjustments apply to the F_b values. These adjustments are not applicable to the values listed in Table 5.

<u>Nominal thickness</u>		<u>2" & 3"</u>	<u>4"</u>
Width	4"	1.10	1.00
	5"	1.10	1.05
	6"	1.15	1.05
	8"	1.15	1.05
	10" & wider	1.20	1.10

- (5) All stress rated grades under these rules are established on a basis that permits cutting graded members to shorter lengths without impairment of stress ratings in the shorter pieces.
- (6) See paragraphs 163-164.4 for conditions applicable to seasoned lumber. In widths of 12" and less in lengths of 24' and less, seasoning is required for all lumber of 2" thickness and less, but has to be specified if desired for other widths and lengths or for thicknesses in excess of 2".
- (7) Grade restrictions established under the SPIB Standard Grading Rules apply the entire length of each piece, and each piece therefore is suitable for use in continuous spans, over double spans or under concentrated loads without the necessity of regrading for special shear or other special stress requirements.
- (8) The allowable unit stresses for all stress rated grades under these rules are for normal loading conditions and apply in all cases other than those for which special exceptions are to be made. Where a member is to be fully loaded to the maximum design stress for many years, either continuously or cumulatively, working stresses 90% of those indicated herein should be used. The stresses may be modified on a similar basis for railroad bridges and other structures that involve unusually hazardous or severe service conditions.
- (9) Compression perpendicular-to-grain values are design stresses for 0.04" deformation. For design stress at 0.02" deformation, use 74% of the corresponding tabulated values.



- (10) The allowable unit stresses and adjustments apply to lumber used under conditions continuously dry, as in most covered structures.
- (11) Lumber 2-1/2" – 4" nominal thickness above 19% (S-GRN) and lumber in service under wet conditions of use or where the moisture content is at or above the fiber saturation point, as when continuously submerged, the recommended design values shall be multiplied by the following factors:

Property	Factor
$F_b \leq 1150$ psi	1.0
$F_b > 1150$ psi	0.85
F_t	1.0
F_v	0.93
F_{cL}	0.67
$F_{c } \leq 750$ psi	1.0
$F_{c } > 750$ psi	0.8
MOE	0.9

- (12) Lumber chemically treated may require adjustments to the recommended design values. Reference should be made to the American Wood Protection Association Standards and the National Design Specification of the American Wood Council.